

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
23 May 2002 (23.05.2002)

PCT

(10) International Publication Number
WO 02/40074 A1

- (51) International Patent Classification⁷: **A61L 27/32**, 27/06, 27/10, A61F 2/30, A61C 8/00
- (54) Title: **ENDOSSEOUS IMPLANT**
- (71) Applicants (for all designated States except US): **UNIVERSITE DE GENEVE** [CH/CH]; 24, rue Général-Dufour, CH-1211 Genève 4 (CH). **ECOLE POLYTECHNIQUE FEDERALE DE LAUSANNE** [CH/CH]; CH-1015 Lausanne (CH).
- (72) Inventors; and
(75) Inventors/Applicants (for US only): **DESCOUTS, Pierre** [FR/FR]; Le Grand Pré bis, F-74160 Neydans (FR). **ARONSSON, Björn-Owe** [SE/CH]; Chemin de la Grande-Gorge 9, CH-1255 Veyrier (CH). **GRÄTZEL, Michael** [DE/CH]; Chemin du Marquisat 7A, CH-1025 St. Sulpice (CH). **VIORNERY, Carine** [FR/FR]; 19, rue Koenig, F-29560 Carantec (FR). **PECHY, Peter** [HU/CH]; Avenue Victor Ruffy 17, CH-1012 Lausanne (CH).
- (52) International Application Number: **PCT/EP01/13364**
- (22) International Filing Date:
19 November 2001 (19.11.2001)
- (25) Filing Language: English
- (26) Publication Language: English
- (30) Priority Data:
PCT/EP00/11510
20 November 2000 (20.11.2000) EP
- (81) Designated States (national): AE, AG, AI, AM, AT, AU (utility model), AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, CZ (utility model), DE, DE (utility model), DK, DK (utility model), DM, DZ, EC, EE, EE (utility model), ES, FI, FI (utility model), GB, GI, GH, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NO, NZ, OM, PH, PL, PT, RO, RU, SD, SE, SG, SI, SK, SK (utility model), SL, TJ, TM, TR, TT, TZ, UA, UG, US, UZ, VN, YU, ZA, ZM, ZW.
- (84) Designated States (regional): ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).
- Published:
— with international search report
— before the expiration of the time limit for amending the claims and to be republished in the event of receipt of amendments
- For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.



WO 02/40074 A1

Endosseous Implant

The present invention relates to a metallic endosseous implant made from titanium or a titanium alloy to be applied to a human or animal bone, said implant having a smooth or rough surface texture, and wherein said surface has been treated with at least one selected organic compound carrying one or more phosphonic acid group [$-P(O)(OH)_2$] or a derivative thereof, preferably as a pharmaceutically acceptable salt or ester or amide thereof. It has been shown that such chemically modified surface surprisingly enhances the bone bonding strength. Implants according to the present invention may be used as prostheses in medicine, more specifically in orthopaedics, for replacing or strengthening broken or diseased bones, and in dentistry, for anchoring artificial teeth and for anchoring of bone anchored hearing prosthesis.

Implants which are used as prostheses in medicine for replacing or strengthening broken or diseased bones or as artificial teeth are known. These implants must be made of a non-corrosive material and must be compatible with the surrounding tissue without producing immunologic reactions effecting rejection by the body. In the following the terms "surface" or "contact surface" refer to the titanium or a titanium alloy implant surface not yet treated according to the present invention and the term "modified surface" to the surface treated according to the present invention.

It is known that to implant devices in the form of screws, plates, nails, pins, and specially formed parts into the skeletal structure of humans and animals as artificial prosthetic is a means for permanent replacement of missing structural parts or as permanent anchoring devices. An

excellent "osseointegration" is required for those situations where the implanted device should remain permanently adhered to the contacting bone surface.

- It is generally known to use titanium metal or titanium alloys for such implants. When carefully produced, the titanium implant with its surface oxide exhibits biocompatibility in the sense that it remains passive for bone regeneration and does not per se induce adverse reactions such as inflammation or soft tissue generation or encapsulation. The interface obtained between the implant and the bone tissue normally consists of a protein layer of about 100 nm to 1 μ m thickness preventing the bone tissue from being in direct molecular contact with the implant.
- The actual state of the art for endosseous implants is based on different approaches, for example (i) the creation of a suitable roughness of the implant surface giving a mechanical interlocking between bone and implant and/or (ii) coating the titanium or titanium alloy surface of the implant, e.g. with an artificial hydroxyapatite for improving the healing process and the bone-implant intimate contact.


- It is known that a high surface roughness on titanium implants increases the mechanical stability of the implant in the bone tissue. Mechanical surface treatment significantly alters the topography, while the surface chemistry remains substantially unchanged. The disadvantages of an implant with a high surface roughness are that a purely mechanical anchoring is very sensible to micromotions which may lead to a deterioration of the mechanical anchorage and that the osseointegration time of the implant is relatively long.

Coating the surface of the implant with an artificial hydroxyapatite decreases the osseointegration time. However, it is very difficult, if not impossible, to produce hydroxyapatite coatings with a long term stability on load bearing implants. The interface between the coating and the implant is often disrupted or the coatings are flaked off.

US 5,733,564 suggests to use selected bisphosphonates which are known drug substances for the promotion of bone tissue formation by coating titanium metal surfaces of prostheses or implants with these compounds.

It has now been found that if the surface of a titanium or a titanium alloy endosseous implant has been treated with at least one selected organic compound as defined herein below carrying one or more phosphonic acid groups or a derivative thereof, preferably an ester, an amide or a salt thereof, as defined herein below, said surface shows a surprisingly improved bone bonding strength and a surprisingly shortened osseointegration time compared to the non treated surface and does not have the disadvantages as known for surfaces having a hydroxyapatite coating.

The present invention is defined in the claims. The present invention specifically refers to an endosseous implant to be applied to a human or animal bone, wherein the surface of the implant is made from titanium or a titanium alloy, said implant having a smooth or rough surface texture, which is characterized in that said surface has been treated with at least one organic compound corresponding to the general formula (I):



(I),

or a pharmaceutically acceptable derivative thereof, which is preferably an ester, an amide or a salt thereof, wherein A means A₁ or A₂, and

A₁ is a residue of a linear, branched or cyclic, saturated or unsaturated, hydrocarbon residue with n carbon atoms, whereby said residue may be substituted by hydroxyl and/or carboxyl and optionally further interrupted by one or more oxygen and/or sulphur and/or nitrogen atoms, carrying p phosphonic acid groups, wherein n is a number from 1 to 70, preferably 1 to 40, preferably 1 to 22, and

when n is 1 and p is 2: A is -CH₂-, or

when n is 1: p is 3 or 4, preferably 3, or

when n is 2 to 10: p is 2, provided each phosphonic acid group or phosphonic acid ester group is bound to a different carbon atom within the same molecule; or

when n is 2 to 10: p is 3, 4, 5 or 6, preferably 3, 4 or 5, preferably 3 or 4; or

when n is 11 to 70: p is 2, 3, 4, 5 or 6, preferably 2, 3, 4 or 5, preferably 2, 3 or 4;

or A means A₂ and

A₂ is a residue of an amino acid or of a sequence of amino acids resp. of a protein or of a polypeptide, preferably a residue of the superfamily of Transforming Growth Factor beta (TGF-β); or a residue of a specific drug molecule, wherein each residue A₂ carries p phosphonic acid groups, and

p is 1 to 6, preferably 1, 2, 3 or 4, preferably 1, 2, or 3, when A₂ is a residue of an amino acid or of a sequence of amino acids resp. of a protein or of a polypeptide; or

p is 1 or 3-6, preferably 1, when A₂ is a residue of a specific drug molecule originally not bearing any phosphonic group, optionally falling under the definition given for A₁.

The present invention further refers to a process for producing the implant according to the present invention which is characterized in that said surface is treated with at least one organic compound of formula (I) or a derivative thereof, which is preferably an ester, an amide or a salt thereof.

It is assumed that the phosphonate compounds as specified herein, especially as acids or salts, form a covalent bond with the surface of the implant thereby improving the osseointegration properties of said surface to a remarkable and unexpected extent. The present invention however is not bound to this explanation.

A₁ preferably is a saturated hydrocarbon residue of the formula $-(C_nH_{2n+2-p})-$, wherein n means 1 to 70, preferably 1 to 40, preferably 1-22. Preferred is the free acid or the salt form of the compound of formula (I), preferably where the pharmaceutically acceptable salt is an alkali salt, preferably of sodium or potassium salt. If the pharmaceutically acceptable ester is used, the isopropyl phosphonate or ethyl phosphonate esters are preferred, examples of such esters are: tetra isopropyl methylenediphosphonate, hexaethyl ethane-1,1,2-triphosphonate, hexa isopropyl butane-1,1,4-triphosphonate, hexaisopropyl pentane-1,1,5-triphosphonate, hexaisopropyl pentane-2,2,5-triphosphonate, hexaisopropyl hexane-2,2,6-triphosphonate,

octaisopropyl propane-1,1,3,3-tetraphosphonate, octaisopropyl heptane-1,4,4,7-tetraphosphonate, octaisopropyl nonane-1,5,5,9-tetraphosphonate.

- The metallic surface of the endosseous implant to be treated according to the present invention may be made from titanium or a titanium alloy as known to be used for the production of endosseous implants. Titanium alloys may be made from titanium and any other metal known to form an alloy with titanium, such as chromium, niobium, tantalum, vanadium, zirconium, aluminium, cobalt, nickel and/or stainless steels. Such titanium metal alloys for making implants are known per se and are described for example in Breime et al., *Metals as Biomaterials*, pp. 1-71 (1998) the contents of which are incorporated herein by reference.
- Implants according to the present invention may be in the form of screws, plates, nails, pins, and specially formed parts and may be used as prostheses in medicine, more specifically in orthopaedics, for replacing or strengthening broken or diseased bones, and in dentistry, for anchoring artificial teeth and for anchoring of bone anchored hearing prosthesis into the skeletal structure of humans and animals. The surface area of the implant which is to be bound to the body tissue resp. bones, may have a smooth or rough surface texture. Such surface textures are known and can be obtained for example by treating the surface mechanically and/or with acids and/or electrolytically and/or with a glow-discharge plasma and/or plasma spraying and/or or by electro machining. Such materials and processes have been described in different publications, for example in B.-O. Aronsson et al., *J. Biomed. Mater. Res.* 35 (1997), pp. 49f., the contents of which are incorporated herein by reference.

Examples of compounds of formula (I) wherein A is a residue of a saturated hydrocarbon are polyphosphonic acids such as methylenediphosphonic acid, ethane-1,2-diphosphonic acid, propane-1,3-diphosphonic acid, propane-1,3-diphosphonic acid, ethane-1,1,2-triphosphonic acid, butane-1,1,4-triphosphonic acid, pentane-1,1,5-triphosphonic acid, pentane-2,2,5-triphosphonic acid, hexane-2,2,6-triphosphonic acid, pentane-1,1,5,5-tetraphosphonic acid, heptane-1,4,4,7-tetraphosphonic acid, propane-1,1,3,3-tetraphosphonic acid, or nonane-1,5,5,9-tetraphosphonic acid.

Examples of compounds of formula (I) wherein A is a residue of a protein resp. polypeptide in the form of a Transforming Growth Factor beta (TGF- β) in which are included the all members of the superfamily of growth factors and particularly the TGF- β 1, TGF- β 2, TGF- β 3, TGF- β 4, and TGF- β 5 as described for example in A.B. Roberts, M.B. Sporn, Handbook of Experimental Pharmacology, 95 (1990) pp. 419-472 or D.M. Kingsley, Genes and Development 8 (1994) p. 133-146, and references therein, where the peptide chain has been modified to contain an alkylphosphonic acid group or a derivative thereof, which is preferably an ester, an amide or a salt thereof. In this sense the compound of formula (I) represents a Transforming Growth Factor beta (TGF- β) as defined by the members of the superfamily of growth factors, preferably the TGF- β 1, TGF- β 2, TGF- β 3, TGF- β 4, and TGF- β 5, wherein each time the peptide chain has been modified to contain at least one alkylphosphonic acid group or a derivative thereof, which is preferably an ester, an amide or a salt thereof.

Examples of compounds of formula (I) wherein A is a residue of a Bone Morphogenic Protein (BMP) (being a

subfamily to the TGF family) e.g., the BMP-2 (BMP-2a), BMP-3, BMP-4 (BMP-2b), BMP-5, BMP-6, BMP-7 (OP-1), BMP-8 (OP-2), BMP-9, BMP-10, BMP-11, BMP-12, BMP-13, as found for example in J.M. Wozney et. al., Science 242 (1988) 1528-1534; A.J. Celeste et al., Proc. Natl. Acad. Sci. USA 87 (1990) 9843-9847; E. Özkaynak et al., J. Biol. Chem. 267 (1992) 25220-25227 ; Takao et al., Biochem. Biophys. Res. Com. 219 (1996) 656-662 ; WO 93/00432 ; WO 94/26893 ; WO 94/26892 ; WO 95/16035 and references therein, where the peptide chain has been modified to contain an alkylphosphonic acid group or a derivative thereof, which is preferably an ester, an amide or a salt thereof. These compounds are incorporated herein by reference. In this sense the compound of formula (I) represents a Bone Morphogenic Protein (BMP), preferably the BMP-2 (BMP-2a), BMP-3, BMP-4 (BMP-2b), BMP-5, BMP-6, BMP-7 (OP-1), BMP-8 (OP-2), BMP-9, BMP-10, BMP-11, BMP-12, BMP-13, wherein the peptide chain has been modified to contain at least one alkylphosphonic acid group or a derivative thereof, which is preferably an ester, an amide or a salt thereof.

Examples of compounds of formula (I) wherein A is a residue of an amino acid are 2-amino-4,4-bis-(diethoxyphosphoryl)-butyric acid as described for example in O. Fabulet et al., Phosphorus, Sulphur Silicon and Related Elements, 101, 225-234 (1995); 2-amino-5-(diethoxyphosphoryl)-pentanoic acid as described for example in I.G. Andronova et al., Russ. J. Gen. Chem. 66, 1068-1071 (1996); 2-amino-4-phosphonobutyric acid as described for example in X.Y. Jiao et al., Synth. Commun. 22, 1179-1186 (1992) and references therein. Further examples are all the principal twenty amino acids as described for example in L. Stryer, Biochemistry, 3rd edition (1988), pp. 17-22, where the amino acid is modified in an analogous way with

an alkylphosphonic acid group or a derivative thereof, which is preferably an ester, an amide or a salt thereof, preferably wherein the compound of formula (I) is one of the principal twenty amino acids, preferably arginine, glycine, aspartic acid, alanine, valine, proline, serine, threonine, cysteine or lysine, wherein the amino acid has been modified to contain at least one alkylphosphonic acid group or a derivative thereof, said derivative being preferably an ester, an amide or a salt thereof. These compounds are incorporated herein by reference.

Examples of compounds of formula (I) wherein A is a residue of a peptide comprise but are not limited to RGD-containing peptides, RGDS-peptides, GRGDS-peptides, RGDV-peptides, RGDE-peptides, and/or RGDT-peptides. Such peptides are described for example in Y. Hirano, J. Biomed. Materials Res., 25 (1991), pp. 1523-1534 or in WO 98/52619 and references therein. Included within the scope of the present invention are also similar peptides known to have specific biological activities such as cell attachment or cell attachment prevention, and which are prepared in analogy with the peptides as mentioned above. In this sense the compound of formula (I) is a RGD-containing peptide, preferably a RGDS-peptide, a GRGDS-peptide, a RGDV-peptide, a RGDE-peptide, and/or a RGDT-peptide, which has been modified to contain at least one alkylphosphonic acid group or a derivative thereof, which is preferably an ester, an amide or a salt thereof.

Preferred compounds of formula (I) are those containing a residue A₂ as defined above, preferably a residue of an amino acid or of a sequence of amino acids resp. of a protein or of a polypeptide, preferably a residue of the superfamily of Transforming Growth Factor beta (TGF- β), preferably a Bone Morphogenic Protein (BMP).

The following steps are recommended to be taken for producing the implant according to the present invention, i.e. for treating the surface of the implant with at least one compound of formula (I) above. The implant is first
5 cleaned in a cleaning bath for removing unwanted molecules resp. impurities from the surface. Preferably the implant is first treated with a degreasing agent, for example an organic solvent such as alcohol, chloroform, and another organic solvent and/or an inorganic detergent such as an
10 aqueous alkaline solution based on sodium hydroxide or potassium hydroxide. Subsequently, the implant is carefully rinsed in pure water, preferably in distilled ultra-pure water, having preferably a conductivity resistance of at least 15 Mohm*cm. After cleaning and
15 rinsing, the implant is dried with flowing nitrogen gas or flowing dry or hot air and stored under controlled conditions. Alternatively after degreasing the implant can be further treated in a glow-discharge plasma for cleaning the surface. The clean surface of the implant is then
20 treated with at least one compound of formula (I) or an ester or a salt thereof, i.e. with at least one such compound or a mixture thereof. The compound or the mixture of said compounds is brought onto the surface of the implant by any suitable means, like brushing, spraying,
25 dipping or evaporation, including glow-discharge plasma assisted vapour deposition. The phosphonic acid compound or the ester or the salt thereof is preferably dissolved in a polar solvent, so that a solution with a concentration of from about 1.0×10^{-5} mol/10 ml to 5×10^{-2}
30 mol/10 ml, preferably from about 5×10^{-4} mol/10 ml to 2.0×10^{-2} mol/10 ml with reference to the weight of the solvent is obtained. Preferably the concentration is such that a partial or full (1 % to 100%, preferably 50 % to 100% of a) monomolecular layer is formed on the implant

surface. The preferred solvent is pure distilled water. The implant is left in contact with the solution for a sufficiently long time, preferably for a few minutes up to a few hours. After that the implant is carefully rinsed
5 with pure water and packed with a plastic or metallic clean packaging material preferably into an air tight packaging which preferably is evacuated or filled with an inert gas such as nitrogen or an inert liquid such as pure water as defined herein above. Said pure water may contain
10 inorganic salts, preferably alkali salts, such as alkali chlorides, sulfates, phosphates, phosphonates, preferably the sodium and/or potassium salts, and/or compounds of the formula (I) or an ester or a salt thereof, preferably in a concentration of from about 1.0×10^{-5} mol/10 ml to 5×10^{-2}
15 mol/10 ml, preferably from about 5×10^{-4} mol/10 ml to 2.0×10^{-2} mol/10 ml of solvent, which preferably is distilled water.

Analytical investigations, e.g. X-ray Photoelectron Spectroscopy analysis (XPS) or NMR, have shown that on
20 contacting the phosphonic acid compound of formula (I) with the titanium surface of the implant, immediate adsorption takes place. A strong bond is formed between the surface and the phosphonic acid compound so that a chemical surface modification is obtained. Several different
25 alkane polyphosphonic acids as mentioned herein above were synthesized. Dental implants produced with these compounds according to the present invention have shown excellent results.

The compounds according to the general formula (I),
30 wherein p is 3 to 6, preferably 3 or 4, and n is 4 to 70, preferably 4 to 40, preferably 4 to 22, the salts or esters or amides thereof are new. Examples of such compounds are butane-1,1,4-triphosphonic acid, pentane-

1,1,5-triphosphonic acid, pentane-2,2,5-triphosphonic acid, hexane-2,2,6-triphosphonic acid, pentane-1,1,5,5-tetraphosphonic acid, heptane-1,4,4,7-tetraphosphonic acid, or nonane-1,5,5,9-tetraphosphonic acid.

- 5 The compounds hexaisopropyl butane-1,1,4-triphosphonate and octaisopropyl heptane-1,4,4,7-tetraphosphonate, resp. a mixture of these compounds, are obtained in that an alkalimetal, preferably sodium, tetra lower alkyl methylenediphosphonate, preferably tetraisopropyl
- 10 methylenediphosphonate, is reacting with at least a stoichiometric amount of a dihalomethane, preferably dibromomethane, in the presence of an organic solvent having no active hydrogen atoms, preferably dry hexane or benzene or toluene.
- 15 The reaction is preferably carried out at a temperature within the range of 30°C to 125°C, preferably 40°C to 110°C, until the reaction is completed, which generally is within a time period of 10 to 48 hours, preferably 18 to 36 hours.
- 20 To the reaction product is then added the purified product of triisopropylphosphite that has been reacted with diisopropyl-3-bromopropane. The obtained mixture of compounds can then be separated in a conventional manner, for example by column chromatography
- 25 In an analogous way, by reacting 1,4-dibromobutane in excess molar ratio in the range 1:6 to 1:0.5 with triisopropylphosphite, surprisingly the new compounds hexaisopropyl pentane-1,1,5-triphosphonate and octaisopropyl nonane-1,5,5,9-tetraphosphonate are produced.
- 30 Further, in an analogous way the hexaisopropyl pentane-2,2,5-triphosphonate and hexaisopropyl hexane-2,2,6-triphosphonate were obtained by reacting equal parts of

tetraisopropylethane-1,1-diphosphonate with diisopropyl-3-bromopropylphosphonate.

The process is further characterised by that these products are hydrolysed to produce the analogous acids by
5 refluxing them in molar excess of HCl for a time comprised within 1 to 12 hours, preferably 1 to 6 hours. The compounds are then preferably dried under vacuum over P_2O_5 .

The following Examples illustrate but do not limit the present invention.

10 Example 1

Methylenediphosphonic acid was synthesized according to US-patent 3,400,176 and B.A. Arbusov, Pure Appl. Chem. 9 (1967), pp. 307-353 and references therein. The compound was characterized by NMR (1H , ^{31}P , ^{13}C), mass spectroscopic
15 elemental analysis and by its melting point. All these data are in accordance with the literature O.T. Quimby et al., J. of Organomet. Chem. 13, 199-207 (1968).

Propane-1,1,3,3-tetraphosphonic acid was synthesized from tetraisopropyl methylenediphosphonate. The tetraphosphonic
20 acidic solution was concentrated under vacuum, dried over P_2O_5 under vacuum. The 1H , ^{31}P and ^{13}C NMR results (D_2O) are in accordance with the given literature data.

In an analogous manner propane-1,3-diphosphonic acid, ethane-1,1,2-triphosphonic acid, butane-1,1,4-triphosphonic acid, pentane-1,1,5-triphosphonic acid, pentane-
25 2,2,5-triphosphonic acid, hexane-2,2,6-triphosphonic acid, pentane-1,1,5,5-tetraphosphonic acid, heptane-1,4,4,7-tetraphosphonic acid, or nonane-1,5,5,9-tetraphosphonic acid, are synthesized.

Example 2

- A) A sample made from titanium in the form of a circular plate of 14 mm in diameter, having a thickness of 1 mm, is produced in a conventional manner. The sample surface is provided with a smooth surface roughness by mechanical polishing with diamond paste according to standard procedures. By Atomic force microscopy the surface roughness was measured to a S_{rms} value of ca 6 nm over a surface area of 400 square microns.
- B) The implant as produced in chapter A) above is then put into an aqueous solution of (i) methylenediphosphonic acid [$1,5 \times 10^{-3}$ mol per 10 ml of distilled water], (ii) ethane-1,1,2-triphosphonic acid [1.2×10^{-3} mol per 10 ml, in distilled water], (iii) propane-1,1,3,3-tetraphosphonic acid [6.2×10^{-4} mol per 10 ml, in distilled water], (iv) 1-hydroxyethylidenediphosphonic acid [1.4×10^{-3} mol per 10 ml, in distilled water] and left there at room temperature for 15 minutes. The implant is then rinsed with pure water and dried.
- The implant prepared according to the preparations B(i), B(ii), and B(iii) are plated with rat bone building cells, osteoblasts. The osteogenesis is measured as (I) the cell proliferation and (II) the bone protein synthesis. Comparative test results are given for the untreated implant. The results are given in Table 1. Analogous results are obtained for all the phosphonic acids given herein above both on a smooth and on a rough surface. Analysis with XPS and ToF-SIMS indicated that a molecular (mono) layer was formed on a titanium surface as well as on a TiO_2 -surface.

Table 1

Preparation	Number of cells* after 4 days (\pm SEM)	Total protein synthesis* after 8 days (cpm \dagger x 10 ⁴ per million cells) (\pm SEM)	Collagen* after 8 days (% of total protein) (\pm SEM)
B(i)	36108 (\pm 2485)	94224 (\pm 8357)	3.18 (\pm 0.17)
B(ii)	40773 (\pm 1263)	104503 (\pm 2863)	3.19 (\pm 0.10)
B(iii)	37290 (\pm 2852)	92361 (\pm 8237)	2.30 (\pm 0.29)
Comparative Test	32560 (\pm 2485)	87842 (\pm 3161)	2.74 (\pm 0.18)

* the numbers are given as an average value from three measurements for each test. \dagger cpm = counts per minute from radio labeled proteins.

The results illustrate the improved osteogenesis of the
5 implants according to the present invention compared to
the non treated implants.

Example 3

Example 2 is repeated with the difference that the implant is
10 treated with ethane-1,1,3-triphosphonic acid which has been
modified by linking the amine terminus of a Glycine molecule
to one of the phosphonate groups.

Example 4


Examples 2 is repeated with the difference that the implant
15 is treat with ethane-1,1,3-triphosphonic acid which is
modified by linking the amine terminus of a GRGDS cell binding
polypeptide to one of the phosphonate groups.

Example 5

Examples 2 is repeated with the difference that the compound according to formula (I) is ethane-1,1,3-triphosphonic acid
5 which is modified by linking the amine terminus (Methionine) of a human Bone Morphogenic Protein type 2 (BMP-2) to one of the phosphonate groups, which gives analogous test results as given in Table 1.

Claims

1. Endosseous implant to be applied to a human or animal bone, wherein the surface of the implant is made from titanium or a titanium alloy, said implant having a smooth or rough surface texture, characterized in that said surface has been treated with at least one organic compound corresponding to the general formula (I):



or a pharmaceutically acceptable derivative thereof, which preferably is an ester an amide or a salt thereof, wherein A means A₁ or A₂, and

- A₁ is a residue of a linear, branched or cyclic, saturated or unsaturated, hydrocarbon residue with n carbon atoms, whereby said residue may be substituted by hydroxyl and/or carboxyl and optionally further interrupted by one or more oxygen and/or sulphur and/or nitrogen atoms, carrying p phosphonic acid groups, wherein n is a number from 1 to 70, preferably 1 to 40, preferably 1 to 22, and

when n is 1 and p is 2: A is -CH₂-, or

when n is 1: p is 3 or 4, preferably 3, or

- when n is 2 to 10: p is 2, provided each phosphonic acid group or phosphonic acid ester group is bound to a different carbon atom within the same molecule; or

when n is 2 to 10: p is 3, 4, 5 or 6; preferably 3, 4 or 5; preferably 3 or 4; or

when n is 11 to 70: p is 2, 3, 4, 5 or 6; preferably 2, 3, 4 or 5; preferably 2, 3 or 4;

or A means A_2 and

5 A_2 is a residue of an amino acid or of a sequence of amino acids resp. of a protein or of a polypeptide, preferably a residue of the superfamily of Transforming Growth Factor beta (TGF- β); or a residue of a specific drug molecule, wherein each residue A_2 carries p phosphonic acid groups, and

10 p is 1 to 6, preferably 1, 2, 3 or 4, preferably 1, 2, or 3, when A_2 is a residue of an amino acid or of a sequence of amino acids resp. of a protein or of a polypeptide; or

15 p is 1 or 3-6, preferably 1, when A_2 is a residue of a specific drug molecule originally not bearing any phosphonate group, optionally falling under the definition given for A_1 .

2. Implant according to claim 1, wherein A_2 is a saturated hydrocarbon residue of the formula $-(C_nH_{2n+2-p})-$, wherein n means 1 to 70, preferably 1 to 40, preferably 1 to 22.

3. Implant according to claim 1 or 2, wherein the pharmaceutically acceptable salt is an alkali salt, preferably of sodium or potassium salt.

25 4. Implant according to any one of the claims 1-3, wherein the pharmaceutically acceptable ester is an alkyl phosphonate, or an ethyl acetate.

5. Implant according to any one of the claims 1-4, wherein the compound of formula (I) is a
30 polyphosphonic acid, preferably selected from

- methylenediphosphonic acid, ethane-1,2-diphosphonic acid, propane-1,3-diphosphonic acid, propane-1,3-diphosphonic acid, ethane-1,1,2-triphosphonic acid, butane-1,1,4-triphosphonic acid, pentane-1,1,5-triphosphonic acid, pentane-2,2,5-triphosphonic acid, hexane-2,2,6-triphosphonic acid, pentane-1,1,5,5-tetraphosphonic acid, heptane-1,4,4,7-tetraphosphonic acid, propane-1,1,3,3-tetraphosphonic acid, and/or nonane-1,5,5,9-tetraphosphonic acid or an ester or a salt thereof.
6. Implant according to claim 4, wherein the compound of formula (I) is an ester, preferably tetra isopropyl methylenediphosphonate, hexaethyl ethane-1,1,2-triphosphonate, hexaisopropyl butane-1,1,4-triphosphonate, hexaisopropyl pentane-1,1,5-triphosphonate, hexaisopropyl pentane-2,2,5-triphosphonate, hexaisopropyl hexane-2,2,6-triphosphonate, octaisopropyl propane-1,1,3,3-tetraphosphonate, octaisopropyl heptane-1,4,4,7-tetraphosphonate, octaisopropyl nonane-1,5,5,9-tetraphosphonate.
7. Implant according to claim 1, wherein the compound of formula (I) is a Transforming Growth Factor beta (TGF- β) as defined by the members of the superfamily of growth factors, preferably the TGF- β 1, TGF- β 2, TGF- β 3, TGF- β 4, and TGF- β 5, wherein each time the peptide chain has been modified to contain at least one alkylphosphonic acid group or a derivative thereof, which preferably is an ester an amide or a salt thereof.
8. Implant according to claim 1, wherein the compound of formula (I) is a Bone Morphogenic Protein (BMP), preferably the BMP-2 (BMP-2a), BMP-3, BMP-4 (BMP-2b),

- BMP-5, BMP-6, BMP-7 (OP-1), BMP-8 (OP-2), BMP-9, BMP-10, BMP-11, BMP-12, BMP-13, wherein the peptide chain has been modified to contain at least one alkylphosphonic acid group or a derivative thereof, which preferably is an ester an amide or a salt thereof.
- 5
9. Implant according to claim 1, wherein the compound of formula (I) is 2-amino-4,4-bis-(diethoxy-phosphoryl)-butyric acid, 2-amino-5-(diethoxy-phosphoryl)-pentanoic acid and/or 2-amino-4-phosphonobutyric acid.
- 10 10. Implant according to claim 1, wherein the compound of formula (I) is one of the principal twenty amino acids, preferably arginine, glycine, aspartic acid, alanine, valine, proline, serine, threonine, cysteine, lysine, wherein the amino acid has been
- 15 modified to contain at least one alkylphosphonic acid group or a derivative thereof, which preferably is an ester an amide or a salt thereof.
11. Implant according to claim 1, wherein the compound of formula (I) is a RGD-containing peptide, preferably a
- 20 RGDS-peptide, a GRGDS-peptide, a RGDV-peptide, a RGDE-peptide, and/or a RGDV-peptide, which has been modified to contain at least one alkylphosphonic acid group or derivative thereof, which preferably is an ester an amide or a salt thereof.
- 25 12. Process for producing the implant according to any one of the claims 1-11, characterized in that said surface is treated with at least one organic compound of formula (I) or an ester or a salt or a mixture thereof.
- 30 13. Implants according to any one of the claims 1-12 in the form of screws, plates, nails, pins, and

specially formed parts and may be used as prostheses in medicine, more specifically in orthopaedics, for replacing or strengthening broken or diseased bones, and in dentistry, for anchoring artificial teeth or for anchoring of bone anchored hearing prosthesis into the skeletal structure of humans and animals.

14. Implant according to claim 13, wherein said implant is packed with a plastic or metallic packaging material, preferably into an air tight packaging which optionally is evacuated or filled with an inert gas or an inert liquid.
15. Implant according to claim 14, wherein said packaging is filled with pure water containing an inorganic salt and/or a compound of the formula (I) or a salt thereof, preferably in a concentration of from about 1.0×10^{-5} mol/10 ml to 5×10^{-2} mol/10 ml, preferably from about 5×10^{-4} mol/10 ml to 2.0×10^{-2} mol/10 ml of the water.
16. The compounds according to the general formula (I) the salts or esters thereof according to any one of the claims 1-11, wherein p is 3 to 6, preferably 3 or 4, and n is 4 to 70, preferably 4 to 40, preferably 4 to 22.
17. The compounds according to claim 16, being butane-1,1,4-triphosphonic acid, pentane-1,1,5-triphosphonic acid, pentane-2,2,5-triphosphonic acid, hexane-2,2,6-triphosphonic acid, pentane-1,1,5,5-tetraphosphonic acid, heptane-1,4,4,7-tetraphosphonic acid, or nonane-1,5,5,9-tetraphosphonic acid, a salt or an ester or an amide thereof.

18. Process for producing the chemical compound in the form of their acid according to claim 17, characterized in that the corresponding ester is hydrolysed in the presence of an acid.

INTERNATIONAL SEARCH REPORT

Application No
PCT/EP 01/13364

A. CLASSIFICATION OF SUBJECT MATTER

IPC 7 A61L27/32 A61L27/06 A61L27/10 A61F2/30 A61C8/00

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 A61L A61F A61C C07F A61K

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal, WPI Data, PAJ, FSTA, INSPEC, COMPENDEX

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	WO 99 11202 A (ICET INC) 11 March 1999 (1999-03-11) page 7, line 2 - line 15	1-6, 9, 10, 12-18
Y	page 8, line 11 - line 16 page 11, line 3 - line 20 example 1 ---	1, 7, 8, 11
Y	WO 92 09697 A (CELTRIX LAB INC) 11 June 1992 (1992-06-11) page 4, line 13 - page 5, line 9 page 14, line 28 - page 15, line 8 --- -/-	1, 7, 8, 11

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents:

- *A* document defining the general state of the art which is not considered to be of particular relevance
- *E* earlier document but published on or after the international filing date
- *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- *O* document referring to an oral disclosure, use, exhibition or other means
- *P* document published prior to the international filing date but later than the priority date claimed

T later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

X document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

Y document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

A document member of the same patent family

Date of the actual completion of the international search

26 April 2002

Date of mailing of the international search report

08/05/2002

Name and mailing address of the ISA
European Patent Office, P.B. 5818 Patentamt 2
NL - 2280 HV Rijswijk
Tel: (+31-70) 340-3040, Tx: 31 651 epo nl,
Fax: (+31-70) 340-3018

Authorized officer

Menidjel, R

INTERNATIONAL SEARCH REPORT

Inq # Application No
PCT/EP 01/13364

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US 5 733 564 A (LEHTINEN RISTO TAPANI) 31 March 1998 (1998-03-31) column 1, line 20 - line 34 column 3, line 11 - line 20 column 3, line 60 - column 4, line 41 claims 1-11 -----	1-6, 9, 10, 12-18
X	US 5 646 134 A (YATES ASHLEY J) 8 July 1997 (1997-07-08) column 2, line 47 - line 67 column 4, line 14 - line 37 -----	1-6, 9, 10, 12-18
X	EP 0 860 213 A (HUELS CHEMISCHE WERKE AG) 26 August 1998 (1998-08-26) page 2, line 50 - line 58 page 3, line 11 - line 55 page 6, line 20 - line 58 -----	1-6, 9, 10, 12-18

INTERNATIONAL SEARCH REPORT

 In Application No
 PCT/EP 01/13364

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
WO 9911202 A	11-03-1999	WO 9911202 A1 US 6129928 A	11-03-1999 10-10-2000
WO 9209697 A	11-06-1992	AU 651421 B2 AU 9141991 A CA 2071912 A1 EP 0513334 A1 WO 9209697 A1 US 5393739 A	21-07-1994 25-06-1992 31-05-1992 19-11-1992 11-06-1992 28-02-1995
US 5733564 A	31-03-1998	FI 92465 B AU 6430794 A CA 2160565 A1 CN 1120811 A DE 69425372 D1 DE 69425372 T2 DE 696923 T1 EP 0696923 A1 WO 9423770 A1 JP 8508661 T	15-08-1994 08-11-1994 27-10-1994 17-04-1996 31-08-2000 01-02-2001 10-10-1996 21-02-1996 27-10-1994 17-09-1996
US 5646134 A	08-07-1997	AU 2374895 A AU 3574799 A BG 63102 B1 BG 100910 A CA 2188030 A1 CN 1146152 A , B CZ 9603055 A3 EP 1197213 A2 EP 0756483 A1 FI 964213 A HR 950239 A1 HU 74911 A2 IL 113361 A JP 9512268 T NO 964441 A NZ 284295 A PL 318552 A1 RU 2161032 C2 SK 133396 A3 TW 406021 B US 5972913 A WO 9528936 A1 US 5891863 A ZA 9503185 A	16-11-1995 19-08-1999 30-04-2001 31-03-1998 02-11-1995 26-03-1997 11-06-1997 17-04-2002 05-02-1997 18-10-1996 30-04-1997 28-03-1997 30-11-1999 09-12-1997 18-10-1996 23-06-2000 23-06-1997 27-12-2000 07-05-1997 21-09-2000 26-10-1999 02-11-1995 06-04-1999 27-12-1995
EP 0860213 A	26-08-1998	DE 19700081 A1 DE 19700082 A1 DE 19700083 A1 DE 19732588 A1 CA 2226132 A1 EP 0860213 A2 JP 10249277 A NO 980018 A US 6248811 B1	09-07-1998 09-07-1998 09-07-1998 04-02-1999 03-07-1998 26-08-1998 22-09-1998 06-07-1998 19-06-2001